

COLOUR CHART

Fugalite® Eco colours

Colour Fastness* GS_c (Daylight)
EN ISO 105-A05 standard

	Colour	Colour Fastness* GS _c (Daylight) EN ISO 105-A05 standard
Classic	01 White	1,5
	02 Light Grey	1
	03 Pearl Grey	1
	04 Iron Grey	1,5
	05 Anthracite	2
	06 Black	2,5
	07 Jasmin	1
	08 Bahama Beige	1
	09 Caramel	1,5
	10 Terracotta	2
	11 Brown	2,5
	12 Walnut	2,5
Design	51 Silver	1,5
	50 Pergamon	1,5
	46 Ivory	1
	45 Limestone	1
	52 Dove Grey	1,5
	44 Cement Grey	1
	48 Coffee	2,5
	38 Husky	1
Colors	47 Mediterranean	1
	15 Ocean	1
	41 Eucalyptus	1,5
	49 Moss	2
	20 Magnolia	1,5
	27 Sunset	1,5
	21 Red	4
23 Yellow	1	
	Extra-fine white	1

Legend

- from 5 to 4 high colour fastness; for internal and external use
- from 3.5 to 3 good colour fastness; for internal and external use
- from 2.5 to 1 limited colour fastness; for internal use

* Samples were exposed for 500 hours to a light spectrum equivalent to natural sunlight at midday, at the height of the summer on the earth's surface in the northern hemisphere. Differences in clarity, saturation and hue as compared to the reference sample kept in the dark in standard conditions are measured.

The resulting colour difference ΔE_c is used to calculate the grey scale intensity values for colour fastness (GS_c), expressed in a range from 5 (maximum fastness) to 1.

Important: the human eye cannot distinguish colour differences in the 5 to 3 range.