















# TIMELESS

## GLAZED PORCELAIN STONEWARE

SPECIFICATION REFERENCE E.N. 14411 . APPENDIX G. GROUP BIA. GL		TEST METHOD	REFERENCE VALUE	DECLARED VALUE
	Dynamic coefficient of friction (section 9.6 ANSI A 137.1 2012)	DCOF	>0,42 wet	> 0,42 MATTE
	Barefoot slip resistance	DIN-51097	-	Cl. A+B GRIP
	Slip resistance with shoes	DIN-51130:2010	-	R11 GRIP
	Glaze crazing resistance	ISO-10545-11	Richiesta / Required / Requite / Gefordert / Requerida	RESISTE / RÉSISTANT / RÉSISTE / ERFÜLLT / RESISTE
	Frost resistance	ISO-10545-12	Richiesta / Required / Requite / Gefordert / Requerida	RESISTE / RÉSISTANT / RÉSISTE / ERFÜLLT / RESISTE
	Resistance to low concentrations of acids and alkali	ISO-10545-13	Come dichiarato dal produttore / See manufacturer's declaration / Selon déclaration du producteur / Entsprechend der Herstellerangaben / Tal como declara el fabricante	GLB SHINY
	Resistance to low concentrations of acids and alkali		Come dichiarato dal produttore / See manufacturer's declaration / Selon déclaration du producteur / Entsprechend der Herstellerangaben / Tal como declara el fabricante	GLA MATTE
	Resistance to low concentrations of acids and alkali		Come dichiarato dal produttore / See manufacturer's declaration / Selon déclaration du producteur / Entsprechend der Herstellerangaben / Tal como declara el fabricante	GLA GRIP
	Resistance to domestic chemicals and additives for swimming pools		GB minimo / GB minimum / GB minimum / GB mindestens / GB minimo	GA
	Resistance to staining	ISO-10545-14	classe 3 minimo / class 3 minimum / classe 3 minimum / klasse 3 mindestens / classe 3 minimo	Cl. 4 MATTE
	Resistance to staining		classe 3 minimo / class 3 minimum / classe 3 minimum / klasse 3 mindestens / classe 3 minimo	Cl. 3 SHINY
	Resistance to staining		classe 3 minimo / class 3 minimum / classe 3 minimum / klasse 3 mindestens / classe 3 minimo	Cl. 3 GRIP
	Length and width: admitted deviation, in %, of the average size of each tile from the production dimensions	ISO-10545-2	±0,6% (±2 mm)	±0,15%
	Flatness (centre curvature / edge curvature / warpage)		±0,5% (±2mm)	±0,2%
	Maximum right-angle deviation, in %, in relation to the corresponding production dimensions		±0,5% (±2 mm)	±0,2%
	Flatness (centre curvature / edge curvature / warpage)		±0,5% (±2mm)	± 0,35% GRIP
	Maximum straightness deviation, in %, in relation to the corresponding production dimensions		±0,5% (±1,5 mm)	±0,1%

	Admitted deviation, in %, of the average thickness of each tile from the production dimensions		±5% (±0,5 mm)	±5%
	Surface quality		Il 95% min delle piastrelle deve essere esente da difetti visibili / At least 95% of the tiles must be free from visible flaws / 95% min des carreaux ne doivent présenter aucun défaut visible / Mindestens 95% der Fliesen müssen frei von sichtbaren / min. el 95% de las baldosas tiene que estar exento de defectos visibles	CONFORME / CONFORMING / CONFORME / KONFORM / CONFORME
	Amount of water absorbed, in percentage	ISO-10545-3	E<0,5%	average value 0,08%
	Bending strength in N/mm2	ISO-10545-4	>35 N/mm2	average value 50
	Breaking strength in N (thickness >= 7,5 mm)		≥1300 Newton	average value 3200
	Resistance to abrasion of glazed tiles	ISO-10545-7	Come dichiarato dal produttore / See manufacturer's declaration / Selon déclaration du producteur / Entsprechend der Herstellerangaben / Tal como declara el fabricante	cl.5 (Calacatta)
	Resistance to abrasion of glazed tiles		Come dichiarato dal produttore / See manufacturer's declaration / Selon déclaration du producteur / Entsprechend der Herstellerangaben / Tal como declara el fabricante	Cl. 3 (Eramosa, Amani Grey, Black deep); cl. 4 (Travertino, Marfil, Bardiglio gray, Ceppo di grè)
	Thermal shock resistance	ISO-10545-9	-	RESISTE / RÉSISTANT / RÉSITE / ERFÜLLT / RESISTE

## NOTES